



Produktprüfung  
Zertifizierung  
Qualitätssicherung

**ECO**  
INSTITUT

ECO-INSTITUT GmbH • Sachsenring 69 • 50677 Köln

Didymos Erika Hoffmann GmbH  
Frau Link  
Alleenstr. 8  
71638 Ludwigsburg

ECO-INSTITUT GmbH  
Sachsenring 69  
50677 Köln

Fon +49-(0)221-931 245 -0  
Fax +49-(0)221-931 245 -33


www.eco-institut.de  
www.eco-info.de  
info@eco-institut.de

Geschäftsführer  
Dr. Hans-Ulrich Krieg  
Dr. Frank Kuebart

Köln HRB 25664  
UstId: DE 811775799

Raiffeisenbank  
Frechen-Hürth  
BLZ 370 623 65  
Konto 1 703 060 010

Akkreditiert ISO/IEC 17025

 **AKS** Akkreditierung: AKS-PL-20708  
Verzeichnis: www.aks-hannover.de  
Staatliche Akkreditierungsstelle Hannover



## TEST REPORT No. 20336-5

<b>Description of sample:</b>	<b>red/purple patterned baby sling without description</b>
Kind of sample:	baby sling
Client:	Didymos Erika Hoffmann GmbH, Ludwigsburg
Sampling:	by client
Arrival of sample at the:	18 December 2008
Date:	13 January 2009
Page:	1
Number of pages:	4
Test program:	According to the guidelines of the International Association Natural Textile Industry (IVN): <ul style="list-style-type: none"><li>• Formaldehyde</li><li>• pH-Value</li><li>• Organotin-compounds</li><li>• Azo dye</li><li>• Heavy metals (Eluat) *</li><li>• Resistance to artificial saliva and sweat *</li></ul>
Testing laboratory:	ECO-INSTITUT GmbH except * * subcontracted

## Formaldehyde

<i>Parameter</i>	<i>Result [mg/kg]</i>	<i>Orientation value [mg/kg]</i>
Formaldehyde	< 20	≤ 20

< = below assessment value

Assessment value: 20 mg/kg

IVN-Orientation value: 20 mg/kg

Test method: DIN EN ISO 14184-1.

## pH-Value

<i>Parameter</i>	<i>Value</i>	<i>Orientation value</i>
pH	6,0	4,5 – 9,0 wool 4,5 – 8,0 other textiles

IVN-Orientation value: wool: 4,5 – 9,0, other textiles: 4,5 – 8,0.

Test method: DIN EN 1413.

## Organotin compounds

<i>Substance</i>	<i>Content [mg/kg]</i>	<i>Orientation value [mg/kg]</i>
Monobutyltin (MBT)	< 0,1	0,1
Dibutyltin (DBT)	< 0,05	< 0,05
Tributyltin (TBT)	< 0,05	< 0,05

< = below detection limit

Detection limits: MBT: 0,1 mg/kg; others: 0,05 mg/kg

Test method: extraction, modified E-DIN 38407-13, GC/MS-quantification.

## Azo dye

<i>Result</i>	<i>Azo-dye</i>	<i>Result [mg/kg]</i>	<i>Orientation value [mg/kg]</i>
negative	---	< 30	30

Ref. results: If the sample contains an amine ref. to the german law (LFGB), dated July 20th 1995, it is documented in the column "results".

negative = Azo dyes banned by the regulation on consumer goods have not been detected in the analyzed sample.

positive = Azo dyes banned by the regulation on consumer goods have been applied upon Manufacture or treatment of the said sample according to the result of analysis.

In case of a result between 25 and 35 mg/kg,

we have to point out, that variations due to method and matrix might occur. Thus a result like that represents a borderline case.

Test methods: *non extractable dyes (native fibres):* in accordance with § 64 LFGB, 82.02-2, in conformity with DIN EN 14362-1; *extractable dyes (e.g. polyester):* in accordance with § 64 LFGB, 82.02-4, in conformity with DIN EN 14362-2

## Heavy Metals

<i>Metal</i>	<i>Content [mg/kg]</i>	<i>IVN-Orientation value [mg/kg]</i>
Antimony (Sb)	< 0,1	≤ 0,2
Arsenic (As)	< 0,2	≤ 0,2
Lead (Pb)	< 0,1	≤ 0,2
Cadmium (Cd)	< 0,05	≤ 0,1
Chromium total (Cr)	< 1	≤ 1,0
Chromium VI (Cr VI)	< 1	≤ 0,5
Cobalt (Co)	< 1	≤ 1,0
Copper (Cu)	< 1	≤ 25
Nickel (Ni)	< 1	≤ 1,0
Mercury (Hg)	< 0,02	≤ 0,02
Selenium (Se)	< 0,5	≤ 0,4

< not detectable, below detection limit

Detection limits: Hg: 0,02 mg/kg; Cd: 0,05 mg/kg; Pb, Sb: 0,1 mg/kg; As: 0,2 mg/kg; Se: 0,5 mg/kg; Cr VI, Co, Cr, Cu, Ni: 1 mg/kg

Test method: Elution of heavy metals from textiles by acidic perspiration (60 min. at 40 °C). Quantitative analysis according to DIN 38406-H22/ICP-MS.


## Resistance to artificial saliva and sweat

<i>Parameter</i>	<i>Result</i>	<i>Orientation value</i>
Resistance to artificial saliva and sweat	Grade 5	Fast <sup>1</sup>

Demand by IVN: fast

Test method: DIN 53160.

Cologne, 13 January 2009



Dr. rer.-nat. Hans-Ulrich Krieg  
(Technical manager)

## Assessment

The test result of the sample “red/purple patterned baby sling“ corresponds with the guidelines of the International Association Natural Textile Industry (IVN).

Remark: The complete audit according to the IVN-Textile Standard has not been performed.

Cologne, 13 January 2009



Sarah Fritschen  
(Project manager)

---

<sup>1</sup> Salvia fastness: „FAST“ for baby and children’s clothing

Note: This report only refers to above described sample. Publishing in parts requires authorization.